

# datasheet

## KYDEX<sup>®</sup> 100

### HIGH IMPACT FIRE RATED SHEET

*Offering superior performance in formability, rigidity, impact resistance, fire retardance, and electrical resistance*

#### GENERAL INFORMATION:

Super tough, durable KYDEX 100, a proprietary alloy sheet, brings new dimensions to thermoformers in: formability, rigidity, breakage resistance, chemical resistance and fire retardancy. This high performance thermoplastic sheet is available in a wide range of standard and customer colors, textures, and sheet sizes. It is Underwriters Laboratories, Inc.® recognized for UL Std 94 V-0/5V and UL 746C and has 18 ft.-lbs./in (953 J/m) Notched Izod impact resistance.

#### FEATURES:

SUPERIOR FORMABILITY – For deep or hard to form parts or where good finished detail is required. KYDEX 100 is unsurpassed.

RIGIDITY – KYDEX 100 is more rigid than most other thermoplastics resulting in parts that will deform less when loaded.

BREAKAGE RESISTANCE – With a high Notched Izod impact resistance, KYDEX 100 offers unsurpassed resistance to breakage.

CHEMICAL RESISTANCE – KYDEX 100 meets the highest standard for chemical resistance for thermoplastic materials.

FIRE RETARDANCE – KYDEX is recognized by Underwriter's Laboratories, Inc.® for Standard 94 V-0 and 5V and UL 746C in all gauges and colors.

THERMOFORMABILITY – Excellent forming properties results in uniform wall thicknesses and crisp detail, plus easy machining and fabricating using conventional methods, further expanding finished part possibilities.

ELECTRICAL PROPERTIES – KYDEX 100 exhibits a Dielectric Strength of 565 V/mil and a Dielectric Constant of 3.13 @1000 Hz, 2.78 @1 MHz, 2.46 @800MHz, 2.42 @1.9 GHz, 2.67 @ 5GHz, and 2.7 @20 GHz.

RIPH- KYDEX is endorsed by the Royal Institute of Public Health for conformance to the standard of Hygienic Merit

Property	Test Method	Typical Value <sup>1</sup>
Specific Gravity	ASTM D-792	1.35
Tensile Strength	ASTM D-638	6,100 psi 42 MPa
Elongation, %	ASTM D-638	160
Flexural Strength	ASTM D-790	9,100 psi 63 MPa
Modulus of Elasticity	ASTM D-790	335,000 psi 2310 MPa
Notched Izod Impact Resistance, @ 73°F (23°C)	ASTM D-256	18 ft.-lbs./in 953 J/m
Rockwell Hardness (R Scale)	ASTM D-785	94
Coefficient of Linear Thermal Expansion	ASTM D-696	4.2x10 <sup>-5</sup> °F 7.56 X 10 <sup>-5</sup> /°C
Heat Deflection Temperature (HDT) @ 264 psi (1.8Mpa) annealed	ASTM D-648	173 °F 79°C
<b>Flammability:</b> Underwriter's Lab. Component Recognition	UL Standard 94 <sup>2</sup>	V-0,5V <sup>3</sup>
Motor Vehicle Safety Standard	MVSS 302	Pass
Federal Aviation Administration	FAR 25.853(a)	Pass <sup>3</sup>
BS 476 Part 6		Class 1
BS 476 Part 7		Class 1
EC 95/28/EG		Pass (1-6 mm)
DIN 5510-2		.9 mm(S4,ST,SR2) 6.5 mm(S4,ST,SR2)
DIN 4102-B1		Pass at .7mm

<sup>1</sup>All values based upon .125" (3.17mm) sheet unless otherwise specified.

<sup>2</sup>Underwriter's Laboratories Inc., File E115252

<sup>3</sup>All gauges .028" (0.71 mm) and above. Not intended for specification purposes.

**Kleerdex Company Customer Service**  
Aiken, SC 29802  
800-325-3133 or 803-642-6864  
FAX: 803-642-6867 or 800-452-0155  
[www.kydex.com](http://www.kydex.com)

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users of our products should make their own tests to determine the suitability of each product for their particular purposes. THE PRODUCTS DISCUSSED ARE SOLD WITHOUT WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE, EITHER EXPRESSED OR IMPLIED, EXCEPT AS PROVIDED IN OUR STANDARD TERMS AND CONDITIONS OF SALE, and buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Kydex® is a registered trademark of Kleerdex Company. ©2001 Kleerdex Company.